

PEAPP Series

Linear Low Density Industrial Polyethylene Tubing

Construction:

Linear low density polyethylene tubing


Applications:

- Transfer of air and liquids in industrial applications
- Chemical transfer lines
- Humidifier fill lines
- Drain lines
- Instrument air lines

Features:

- Economical and lightweight
- LLDPE resin provides excellent environmental stress crack resistance
- Six colors
- Excellent resistance to solvents
- Chemically inert
- O Resistant to sunlight and other forms of ultra-violet radiation (black only)
- O FDA Type 1, Class A, category 4 polyethylene resin (complies with FDA 21 CFR 177.1520 for olefin polymers (par (c) 3.2a)). Not NSF Certified

How To Order



Note: 4mm tubing is suitable for use with 5/32" SMC One-touch fittings as is 8mm tubing and 5/16" fittings. 4, 6, 8, 10 and 12mm are commonly available in black, blue and natural only, other colors are special order.

10

ø10mm ø12mm



Weight

	Inch Sizes		Metric Sizes			
OD	Package Length (in)	Package Weight (lbs)	OD	Package Length (in)	Package Weight (lbs)	
	100 🔾	1.2	4mm	100 🔾	0.6	
1/4"	250	3		250	1.5	
1/4	500	6		500	3	
	1,000	12		1,000	6	
	100 🔾	2.3		100 🔾	1.1	
3/8"	250	5.75	6mm	250	2.75	
3/0	500	11.5		500	5.5	
	1,000 🔾	23		1,000	11	
	100 🔾	3.4	8mm	100 🔾	1.5	
1/2"	250	8.5		250	3.75	
	500	17		500	7.5	
	100 🔾	5		1,000	15	
5/8"	250	12.5		100 🔾	2.1	
	500	25	10mm	250 * •	5.25	
			10111111	500	10.5	
				1,000	21	
				100 🔾	2.5	
			12mm	250 * •	6.5	
				500	13	

*Note: Special order only

○ Bagged ● Reel

Specifications - Inch

Nominal OD (in)	Nominal ID (in)	Nominal Wall (in)	Dodina	Working Pressure @ 70°F (20°C) (in)		Service Temp Range	Hardness
0.25	0.17	0.04	1.25	150	450	-50°~	Shore A
0.375	0.25	0.063	2	150	450	+140°F	98A,
0.5	0.375	0.063	2.5	125	375	(-45°~	Shore D
0.625	0.5	0.063	3	100	300	60°C)	55D

Applicable SMC Fitting Series: KQ2, KQG2, KQB2, KG, KB, KS, KX, DMK, KDM Note: Fittings are not FDA/NSF compliant

Specifications - Metric

openioni in an in							
Nominal OD (mm)	Nominal ID (mm)	Nominal Wall (mm)	Bend Radius (mm)	Working Pressure @ 70°F (20°C) (psi)	3:1 Burst Pressure (psi)*	Service Temp Range	Hardness
4	2.5	0.75	25.4	180	540	0	
6	4	1	31.8	150	450	-50°~	Shore A
8	6	1	38	150	450	+140°F - (-45°~ 60°C)	98A, Shore D 55D
10	8	1	51	125	375		
12	9	1.5	63.5	100	300	00 0,	002

Applicable SMC Fitting Series: KQ2, KQG2, KQB2, KG, KB, KS, KX, DMK, KDM Note: Fittings are not FDA/NSF compliant

General Specifications

Goriora: Opocinications		
Operating Fluid	Air, Water, Compatible chemicals	
Operating Temperature	-50 to +140°F (-45 to +60°C)	
Material	Linear Low density polyethylene	
Hardness	Shore A 98A, Shore D 55D	

Note: Working pressure decreases as temperature increases. Pressure ratings can only be obtained with proper coupling procedures. Because we continually examine ways to improve our products, we reserve the right to alter specifications without prior notice.